SLEEP BAMBU

Porcelain Tile



SIZES

		PIECES PER CARTON
6 x 24 Field Tile	18.4	18

TRIM

TYPE	NUMBER	SIZE	PCS. PER CARTON
Bullnose	S-43C9	6 × 24	11

COMMERCIAL USAGE

		INTERIOR			
	RESIDENTIAL	LIGHT COMMERCIAL	_ COMMERCIAL	RESIDENTIAL	COMMERCIAL
Floors/Patios	✓	✓	✓	~	✓
Walls/Backsplashes	✓	✓	✓	~	✓
Countertops	~	~	✓	~	✓
Pool Decking	~	~	✓	~	✓
Pool Linings	~	~	✓	~	✓

Suitable for exterior applications in freezing and non-freezing climates when proper installation methods are followed

NOTES

Special care should be taken when grouting with dark pigmented colors. A grout release is recommended to prevent finely powdered pigments from lodging in the pores of the surface. Use of a latex modified thinset is recommended for installation.

Special care needs to be given when installing tiles 20" and larger. Please refer to www. tileoptima.com/LargeTiles for information.

Since there are variations in all fired ceramic products, tile and trim supplied for your particular installation may not match these samples. Final color selection should be made from actual tiles and trim and not from tile and trim samples or color reproductions. Manufactured in accordance with ANSI A137.1 standards.

For additional information, refer to "Factors to Consider" at www.tileoptima.com/CommercialFactors.

Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.

SHADE VARIATION



HIGH (V3)

Color variation from tile to tile and within each tile.

INSTALLATION

THICKNESS	GROUT JOINT RECOMMENDATION		
3/8"	1/8" (3/16" when rectangular sizes are used in a staggered brick-joint pattern, where the overlap does not exceed 33%)		

DYNAMIC C.O.F. (WET): 2

The higher the rating, the higher the slip resistance.

I < 0.42
2 ≥ 0.42

STATIC C.O.F. (WET): 2

1 0.50 - 0.59

2 ≥ 0.60

TEST RESULTS

	ASTM#	Textured Result	Unpolished Result
Water Absorption	C373	< .05%	< .05%
Breaking Strength	C648	> 450 lbs	> 450 lbs
Scratch Hardness	MOHS	8	8
Chemical Resistance	C650	Resistant	Resistant
Dynamic C.O.F.	A137.1	Wet: ≥ 0.42	Wet: ≥ 0.42
Static C.O.F.	C1028	Wet: ≥ 0.65 Dry: ≥ 0.80	Wet: ≥ 0.60 Dry: ≥ 0.70

