

## 10,00 mm / COLOURED BODY PORCELAIN STONEWARE

	Reference standard E.N. 14411 . Appendix G. Group BIa. GL	Test method	Reference value	Declared value
	Dynamic coefficient of friction	ANSI-137-1	-	MEETS REQUIREMENT
	Chemical resistance	ASTM-650	-	NOT AFFECTED
	Resistance to freeze	ASTM-C1026	-	RESISTANT
	Surface abrasion	ASTM-C1027	-	PEI IV-V
	Stain Resistance	ASTM-C1378	-	NOT AFFECTED
	Water absorption	ASTM-C373	-	MEETS REQUIREMENT
	Breaking strength	ASTM-C648	-	≥ 400